

CURING



Various curing times for the CiP Product range

Confalt Grouted Macadam as well as our other products and systems develop strength very quickly, the minimum time for trafficking depends upon the environment, temperature, vehicles operating the site and loadings imposed onto the surface.



Exposure	25°C	20°C	15°C	10°C	5°C
Light pedestrian traffic Confalt & Monoconfalt	10 Hours	12 Hours	1.5 Days	2 Days	3 Days
Light pedestrian traffic Ferroplan & Contop	13 Hours	16 Hours	1 Days	1.5 Days	2 Days
Freezing to below 40°C Cutting of joints/drilling Wheeled traffic Point loading >40Mpa	19 Hours	1 Day	1.5 Days	2 Days	3 Days
Steam cleaning	1.5 Days	2 Days	3 Days	4 Days	7 Days
Epoxy coating	1.5 Days	2 Days	3 Days	4 Days	7 Days
Heating up to 250°C ¹	3 Days	4 Days	5 Days	8 Days	13 Days
Contact with oil	4 Days	5 Days	7 Days	10 Days	17 Days
Treatment with Curing cleaner ²	6 Days	7 Days	9 Days	14 Days	24 Days

Trafficking any product before the completion of the recommended curing period can lead to cracks and deformation in the floor or pavement. This is can be dangerous and may also invalidate any warranties agreed. Minimum curing temperature is 5°. Items 1 & 2 are applicable to Contop and Ferroplan only.

For any further information on any of our products and services visit www.cipltd.co.uk, email us: sales@cipltd.co.uk or contact us on 01480 216800 and our sales and technical team will be happy to assist you further.